

Greenboard ASLAN C 60

Blackboard ASLAN C 61

The blackboard films for classic chalk

Different hard and smooth surfaces turn into a trendy memoboard with this self-adhesive blackboard film. It can be written on with chalk as often as you like. In facilities such as offices, nurseries and schools or private homes walls turn easily into blackboards with frequently changing writings.

Greenboard ASLAN C 60 – green
Blackboard ASLAN C 61 – black

For any further information please contact our technical advisory service:
+49 (0) 2204.708-80

Construction

face-film:	PVC	
thickness:	~ 160 µm	
adhesive:	acrylic pressure adhesive	thickness: ~ 25 g/m ²
release liner:	silicone paper	square weight: ~ 65 g/m ²

Characteristics

adhesive strength: (ASTMD-903)	immediately:	~ 6 N/25 mm
	after 1 week:	~10 N/25 mm
dimensional stability:	applied onto acrylic glass after 24 hours at 70° C	insignificant longitudinal shrinkage
temperature:	application temperature:	min. 15°C
	service temperature range:	-30 °C up to +80 °C
combustibility:	Stuck on aluminum, the film is self-extinguishing	
minimum durability:	2 years outdoors in Middle European climate, vertical exposure	

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49 (0) 2204.708 80 · fax +49 (0) 2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN®

EXPERTISE IN SELF-ADHESIVE FILMS

Greenboard **ASLAN C 60**

Blackboard **ASLAN C 61**

Processing

- printability:** The material is digitally printable with UV curable inks as well as screenprinting inks. After the printing process with screenprinting inks the print has to dry out for at least 48 hours.
- application:** Application dry or wet. If applied wet, a whitening of the adhesive can occur but will fade away after a couple of days depending on the weather and temperature.
- For a wet application we recommend the transfer liquid ASLAN TL10.
- storage life:** Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 03|2015

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49 (0) 2204.708 80 · **fax** +49 (0) 2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN® 
EXPERTISE IN SELF-ADHESIVE FILMS