

REFLEX SILVER

SPECIFICATIONS

Composition	Average Thickness	Q Carrier	& Certifications			
PU	160-170 microns	Adhesive polyester	REACH n° 1907/2006/EU			
			OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 VEGANOK AZIENDAN. 1004			

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS ↓			TRANSFER SETTINGS ↓			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	from 70 to 100 with new blade, 110 with used blade	20 cm/sec	5+10 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	warm

- → Mirror cut the design
- → Weed excess material
- > Place the design on the garment
- → Heat apply at the conditions shown above
- → Peel carrier warm

PRODUCT HIGHLIGHTS

- → High retroreflectivity power
- → Adhesive carrier helps cutting small details
- → Easy to cut and weed
- → Follows EN ISO 20471 regulation
- NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ⊳ Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 year	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com For further information, please contact our Sales Office.



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



